

Polyprop Non-Tear Outdoor Poster W/W 200mic

An anti-curl and tear resistant white polypropylene film. Excellent colour performance, and eco-friendly as it is 100% PVC free. Ideal for indoor applications such as roller banner graphics, display panels, and posters and other POS applications.

Suitable for use with:



Order Code	W (mm)	L (mm)	Thickness (ums)
ISB275579	1070	50	200
ISB275582	1270	50	200
ISB275968	1270	100	200
ISB275585	1520	50	200
ISB275965	1520	100	200

Polyprop Non-Tear Outdoor Poster W/W 200mic

FEATURES	UNIT	TEST METHOD	RESULT
Substrate	Polypropylene Film		
Thicknes	Mic	NA	200 ±5
Weight	g/m2	NA	170 ±5
Opacity	%	GB/T 1573-1988	≥95
Whiteness (60°)	%	GB/T 8940.1-1988	95 ±5
Gloss	Gs	GB/T 9754-2007	6.0 ±1.0
LAB Value	L	GB/T 17934.1-1999	98.81
	A		0.41
	B		1.06
	ΔE		≤1.0
Tensile Strength (MD)	Mpa	GB/T 12914-1991	≥110
Tensile Strength (CD)	Mpa		≥50
Storage Temperature	°C	NA	20-28
Storage Humidity	%	NA	25-60

NOTE: Information listed above is based on our general experience and observation and is given in good faith and does not constitute terms or part of any contract. We will not accept responsibilities with respects to factors outside our knowledge, including direct, indirect or consequential loss. Values without tolerance statements are values with a tolerance of ±5%. Media will often have a natural base, therefore there can be variances from batch to batch. Shelf life is 2 years, storage temperature 15-25 °C, RH 40-60%. Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours prior to printing. We always recommend a test print and the customer is deemed to have ensured suitability of the material for the application intended and assumes all associated risks and liabilities in connection with specifying, using or not being able to use any product. Always hem edges when used in hanging or suspended applications by high-tack banner tape or welding. Grommets or eyelets should always be inserted in double-hemmed edges, four layers at corners. Remember that sewing in some applications can affect the integrity of the media. Technical specifications may change without notice. E & OE.